



IPEMA Playground Surface Report

Participant: RB Rubber Products, Inc.				Test Date: 9/20/01			
Product Number/Name: Bounce Back 2 1/2"				<input checked="" type="checkbox"/> Initial Test			
Job No: 061786				<input type="checkbox"/> Follow-up Test			
Sample selection date: 8/8/01				Previous Test Date:			
Rating (as specified by Participant): Thickness 2 1/2" Critical Height 6' FT.							
Drop #	Specified Drop Height	-1°C		23°C (Ambient)		49°C	
		HIC	G-Max	HIC	G-Max	HIC	G-Max
1	6'	693.67	128.86	708.84	128.61	677.79	127.36
2	6'	755.42	136.57	762.79	137.56	749.71	138.56
3	6'	751.21	136.82	793.55	140.55	759.03	140.55
Average		753.31	136.69	778.17	139.03	754.37	139.55
1 Foot Over							
1	7'	1003.80	154.48	936.52	148.51	1045.34	158.71
2	7'	1122.59	168.66	1060.08	163.43	1055.99	164.43
3	7'	1116.27	169.40	1023.42	159.70	1052.63	162.94
Average		1119.43	169.03	1041.75	161.56	1054.31	163.68
1 Foot Under							
1	5'	503.35	109.95	514.17	108.71	460.12	102.74
2	5'	559.07	118.66	543.36	113.93	497.18	108.71
3	5'	548.09	116.92	540.33	113.93	509.99	110.95
Average		553.58	117.79	541.84	113.93	503.58	109.83

Sample in complete compliance with standard at rating specified? Yes No
 This sample was tested by me on the date stated above. This data sheet provides an accurate representation of the test results.

Signature: 
Test Technician
 Date: 9/21/01

Reviewed by: 
 Date: 9/21/01

DETROIT TESTING LABORATORY, INC. USE ONLY

DTL Job No.: 061786
 Reviewed/ Witnessed By: Caroline Riddock

Date Received: _____
 Date Reviewed: 9-26-01