

Rubber Mat Specifications

Produced in the USA

MATERIAL	SBR bonded granular black recycled rubber and polymer binding agents		
THICKNESS / WEIGHT	(Nominal) 3/4" (3.8 lbs./sq. ft.) 1/2" (2.7 lbs./sq. ft.) 3/8" (2.0 lbs/sq. ft.)		
APPEARANCE	Flat One Side Anti-Skid, Wire mesh texture surface on opposite side Both Sides Non-Porous		
COLOR	Black, Natural (with white flec), or Black with flecks of colored EPDM rubber		
DENSITY	ASTM D 3676	60 LBS/FT squared	
TENSILE STRENGTH	ASTM D 412	Minimum 300 psi	
ULTIMATE ELONGATION	ASTM D 412 on 1/8"	83 % minimum	
HARDNESS	ASTM D 2240	Shore A 60 + / - 5	
COEFFICIENT OF FRICTION	ASTM D1894	0.960	
FLAMMABILITY	Passes Federal Flammability Standard Doc FF 1-70 CPSC		
FLAME SPREAD	(UL 94 Standard, Horizontal Burning Test for Classifying Material 94HB)	0.495"/MIN on 3/4" thick mat	
DIMENSIONAL STABILITY	+0.242% at two hours @ 60°C -0.092% at 48 hours @ 20°C & 65% Rel. Humidity		
CRITICAL RADIANT FLUX	ASTM E648-94a	0.11 watts/sq. cm	
THERMAL RESISTANCE	R-Value	1/4": 0.18 1/2": 0.27 3/8": 0.36 3/4": 0.54	
THERMAL RESISTIVITY	.72 (all thicknesses)		
THERMAL CONDUCTANCE	1/4": 5.55 1/2": 3.70 3/8": 2.78 3/4": 1.85		
THERMAL CONDUCTIVITY	K-Value 1.39 (all thicknesses)		
TEAR RESISTANCE (ppi)	ASTM D624	150	
COMPRESSION & RECOVERY	ASTM D575	Immediate 98.1% After 24 hours 99.2% After 48 hours 99.4% After 72 hours 99.7% After 96 hours 99.7%	
ACCELERATED WEATHERING Carbon Arc Weatherometer	Fed-Std-191 Method 5804 except with filters removed for the test	Unexposed	Full Exposure
	Tensile, psi	499	344
	Elongation, %	145	70